

## Rubber sponge product guide

Grade name	Dimension	Density	Hardness	Ref.
HE-8	55 to 60mm by 1m by 2m	80 kg ± 10%	7 to 12	EPDM sponge ASTM 2A1
HE-9	62 to 66mm by 1m by 2m	90 kg± 12%	10 to 14 dgr.	EPDM sponge ASTM 2A1
HE-10	56 to 60mm by 1m by 2m	105 kg± 12%	12 to 16 dgr.	EPDM sponge ASTM 2A1
HE-15	56 to 60mm by 1m by 2m	120 kg± 10%	14 to 19 dgr.	EPDM sponge ASTM 2A2
HE-15grey	56 to 60mm by 1m by 2m	115 kg± 10%	12 to 16 dgr.	EPDM sponge ASTM 2A2
HE-15wh	56 to 60mm by 1m by 2m	115 kg± 10%	12 to 16 dgr.	EPDM sponge ASTM 2A2
HE-16SF <sufur-free>	48mm to 53mm by 1m by 2m	125 kg± 10%	18 to 23 dgr.	EPDM sponge ASTM 2A2
HE-17	52 to 55mm by 1m by 2m	160 kg± 10%	16 to 22 dgr.	EPDM sponge ASTM 2A2
HEF-18	47 to 51mm by 1m by 2m	125 kg± 10%	17 to 21 dgr.	Flame retardant EPDM sponge



HC-20	47to 51mm by 1m by 2m	130 kg± 10%	18 to 23 dgr.	CR sponge ASTM 2C2
HC-20grey	47to 51mm by 1m by 2m	130 kg± 10%	16 to 21 dgr.	CR sponge ASTM 2C2
HERS-20	47 to 51mm by 1m by 2m	115 kg± 10%	18 to 23 dgr.	Eco flame-retardant rubber sponge
HEV-EP	43 to 46mm by 1m by 2m	110 kg± 10%	28 to 35 dgr.	EVA blended with EPDM
HEL-01	48 to 54mm by 1m by 2m	80 kg± 10%	No hardness (open-celled)	Open-celled EPDM
HEL-02	48 to 54mm by 1m by 2m	110 kg± 10%	No hardness (open-celled)	Open-celled EPDM
HEL-03	48 to 54mm by 1m by 2m	85 kg± 10%	Semi open- celled	Semi open-celled EPDM
HEL-04	28 to 32mm by 1m by 1.5m	240 kg ± 10%	Open-celled (high density)	Open-celled EPDM
HEV-HB	28 to 32mm by 1m by 1.5m	110~ kg ±10%	25 to 50	High-ball- rebound sponge
HK-Puff	25 to 30mm by 0.8m by 1.2m	150 kg ±10%	Under 10	Cosmetic puff material

cf. density: kg/cubic m, hardness: shore C hardness tester

\*We can supply each grey and beige colored products if there's a customers request

